

## Epoxy.com Product #699 MMA

[Home](#) [Product Catalog](#) [About Us](#) [Chemical Resistant](#) [Epoxy Coatings](#) [Flooring](#) [Installation](#) [Joints](#)  
[Mortars & Grouts](#) [Primers & Sealers](#) [Specifier's Info](#)  
[Structural](#) [Waterproofing](#) [MSDS & Tech Data](#) [Ordering Info](#)

**The Right Product for the Right Job Since 1980**



[\[Contact Us\]](#)

---

## Epoxy.com Product #699

**Low Viscosity Methyl Methacrylate (MMA) Sealer**

**Chemical Resistant Sealer Top Coating - Superior Flow & Leveling,  
Scratch Resistant**

---

### Description

**Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer** is a 100% reactive, low viscosity methyl methacrylate resin developed as a chemical resistant sealer/topcoat. Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer cures to a hard, scratch and wear resistant surface and is specifically designed for dry service in areas subjected to high traffic such as manufacturing areas, aisles, lobbies, service areas, and numerous other applications.

### Advantages

- UV Resistant
- Superior Scratch and Wear Resistance
- Higher Temperature Resistance

- Superior Chemical Resistance.
- Lower Viscosity - Excellent Flow for Leveling
- Fast Setting - Less than 1 Hour
- 100% Reactive

## Considerations

- Concrete must be clean and free of all oil, grease, paint, dirt, sealers, laitance and any other foreign material that might interfere with proper bonding.
- Do not store **Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer** in direct sunlight, storage temperature must be less than 80 ° F.
- On or below grade applications should have a moisture vapor barrier under the slab. Maximum vapor transmission must be less than 3 lbs per ASTM F-1869 and less than 80% RH per ASTM F-2170.

## Composition

**Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer** is a 100% Solids Methyl Methacrylate (MMA).

## Surface Preparation

Good surface preparation is the first necessary step to successful installation of all Resinous Flooring System. All substrates must be clean and free of all oil, grease, paint, dirt sealers laitance and any other foreign matter that may interfere with proper bonding. Follow the directions for surface preparation as outlined in [Epoxy.com Surface Preparation Guide](#).

## Color Selection

Can be used clear (with a slight blue tint). Color packs are available in selected colors. Color pack mix ratio is 1 QT color pack per 5 gallon pail of **Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer and Top Coating Resin**.



## Mixing and Installation

**Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer and Top Coating Resin** requires the adding of [Epoxy.com Product #695 Hardening Powder](#). to start the hardening process. The amount of hardener must be adjusted to the respective surface temperature (see table below). At temperatures below 40°F, Epoxy.com Product #696 Accelerator must be used, contact Epoxy.com Technical Support for a recommended dosing.

In order to achieve the best curing it is necessary to apply **Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer** with a short nap roller. Coating thickness should be a minimum of 10 mils and maximum of 20 mils (80-160 sq ft/gal.) depending on the profile of the base material. One hundred (100) sq ft/gal. is average. If the coating exceeds 20 mils, the top coat may remain visibly blue or yellow and surface cracks are possible. It is best to spread material with a notched trowel or squeegee to the desired thickness, and roll in one direction, then roll in a 90° pattern. This will reduce the occurrence of roller marks in the top coat.

Temp. (°F) of Resin, Air & Floor Surface	Hardener % by Wt. Based on Wt. of #699 Resin	Hardener by Vol. (oz.) Based on Gallon of #699 Resin	Pot Life (min.)	Hardness Time (min.)
+40	1.5	3	Approx. 40	Approx. 55
+50	1.5	3	Approx.	Approx. 40

				30	
+60	1.5	3		Approx. 25	Approx. 35
+70	1.0	1.8		Approx. 15	Approx. 20

Hardener concentration greater than 2% by weight or 4 oz. by volume might lead to discoloration (yellowing). Epoxy.com recommends waiting 2 hours between coating and sealing. Coating work has to be continued after the ***complete hardening*** of the previous layer.

## Physical Properties

Basic Material	Methyl Methacrylate Resin (MMA)
Percent Reactive	100%
Appearance	Clear Low Viscosity Liquid (with slight blue cast)
Viscosity, cps@ 73°F	185-195
Weight per Gallon	8.35 lbs
Recoat Time	2 hours±
Pot Life Min (Varies with Temp)	15-40
Cure Rate (min)	20-55
Heat Resistance	216°F
Shore D Hardness	75-80

## Cleanup

Clean tools and equipment with lacquer thinner or MEK. Consult Material Safety Data Sheet for safety and health precautions.

## Coverage

100 square feet per gallon, average.

## Availability

Contact Epoxy.com Customer Service Department

## Maintenance

**Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer** is considered to be a very low maintenance flooring system. With some textures and conditions it may have to be cleaned by bristle brush or low pressure wash. Due to the thermoplastic character of Methyl Methacrylate (MMA) resins, you may get black marks from fork lifts and tire skidding.

## Storage

Store **Epoxy.com Product #699 Low Viscosity Methyl Methacrylate (MMA) Sealer** in a cool and dry place, below 80°F, out of direct sunlight. Do not store near open flame or food. Shelf life is 4-6 months in the original unopened containers.

## Tips

Adequate cross ventilation should be provided. Good ventilation during the processing ensures a good cross linking and hardening. Read, understand and follow Material Safety Data Sheets and Application Instructions prior to use.

Use only as directed. If substrate and/or material temperature is above 90°F, DO NOT apply material.

## Technical Support

Call Epoxy.com Technical Support Department with any technical support questions.

Proper mixing and installation is critical to the optimal success of all product. See [Installation Tips](#), [Techdata](#), & [MSDS](#) for more details on our products. Be sure to contact us with any questions and/or concerns that you have.

For more information please contact:

## Epoxy.com

A Division of [Epoxy Systems, Inc](#)

20774 W. Pennsylvania Ave.

Dunnellon, Florida 34431

[Hundreds of Systems](#).

Since 1980 - Over 33 years

Florida & Vermont

USA

**Customer and Technical Support Hours: 9AM-4PM Eastern Time (6AM-1PM Pacific Time).  
Closed 12 Noon-1PM Eastern Time for Lunch**

**321-206-1833 Customer Service - Ordering and Order Status**  
**Katey Fontaine, VP - Customer Service Director**  
[sales@epoxy.com](mailto:sales@epoxy.com)

**Technical Support**  
**352-533-2167 Norm Lambert, President - Technical Support Director**  
[info@epoxy.com](mailto:info@epoxy.com)

**352-489-1666 Accounting and Administration**  
**Debby Lambert, CEO, and CFO**  
[office@epoxy.com](mailto:office@epoxy.com)

**352-489-1625 Fax line to all Departments**



Copyright © 1994-2015 - Epoxy Systems Inc. DBA Epoxy.com - Commercial, Industrial, and Residential Resins Since 1980

[Home](#) [Sales Terms](#) [MSDS &Tech Data](#) [Online Ordering Authorization Form](#) [Add this page to Favorites](#)

/

[Secure Login](#)