



Epoxy.com Product #720

Product #720 Cove Paste Binder Method

Installation Instructions – Cove Base

I. GENERAL INFORMATION

Most Epoxy.com FLOORING SYSTEMS can be installed with an integral cove base to provide seamless wall to floor protection. The outline below explains mixing and installation procedures for each type of system.

II. SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Epoxy.com Surface Preparation Guide**. Specific attention should be paid to the following:

- A. Concrete placement
- B. Curing and finishing techniques of the concrete substrate
- C. Age of concrete
- D. Previous contamination of the substrate
- E. Present condition of the substrate

Also, the temperature and humidity conditions of the area to receive the flooring system should be checked. An optimum room temperature of 75°F with a minimum slab temperature of 50°F is required for proper cure of the resin flooring system.

III. COVE BASE FOR Epoxy.com Product #15 QUARTZ SYSTEMS

Installations of an integral cove base with **Epoxy.com Flooring** is normally terminated at the floor line by cutting a straight line at the bottom of the cove and installing the system up to that point. The top of the cove can be terminated with a divider strip. Alternate method involves masking a line with Duct Tape at the top of the cove. If using the duct tape method, be sure to remove the duct tape before the cove sets up too much to remove the duct tape properly.

A. Material Quantities

1. [Epoxy.com #899 Primer](#) / *Low Modulus Binder* 1 gallon
2. *Epoxy.com #720 Cove Paste Binder* 1.25 gallons
3. [Epoxy.com Quartz Granules](#) 100 pounds
4. *Epoxy.com #60 Cove Powder* 1 quart

Recommended batch quantities

- 1 Quart *Epoxy.com #720* part A & 1 cup *Epoxy.com #720* part B
2. 24 pounds *Epoxy.com Colored Quartz Granules*
3. 1 Cup *Epoxy.com # 60 Cove Powder*

Estimated Batch Coverage: 22-25 lineal feet at 1/8"

B. Installation--Priming

It is very important to prime the wall surface prior to installing cove base. Priming insures maximum adhesion to the prepared substrate and helps mixed cove material to "hang" on the wall.

1. Mixing ***Epoxy.com #899*** Low Modulus Epoxy Primer

- a. Stir each component prior to mixing.
- b. Mix two (2) parts by volume of Part A (Base) with one (1) part by volume of Part B (Hardener) for three minutes with a low speed electric drill mixing paddle.
- c. If thinning is desired, add no more than one pint of xylene per gallon of epoxy at time of mixing.
- d. ***Mix only that amount of material that can be used in 40 minutes.***

2. Application--Brush primer onto the wall surface.

3. Allow Primer to tack-up.

C. Installation--Cove Base

1. Mixing ***Epoxy.com #720*** Cove Paste Binder, Quartz Granules, & Cove Powder

- a. Stir each component prior to mixing.
- b. Mix four (4) parts by volume of Part A (Base) with one (1) part by volume of Part B (Hardener) for three minutes with a low speed electric drill mixing paddle.
- c. Transfer to KOL mixer and add *Epoxy.com Cove Powder* to the premixed *Epoxy.com #720*.

Note: Epoxy.com recommends the use of a KOL Mixer when preparing cove base material. Insufficient mixing of cove base material will result in a stiff, dry, and hard to trowel blend that does not have sufficient wetting of aggregate to insure proper bonding to the substrate.

d. Continue mixing while adding *Epoxy.com Colored Quartz Granules*.

e. Mix resin/aggregate mortar for 3 to 4 minutes or until aggregate uniformly is wet.

2. Application

a. Trowel cove base mixture vertically onto primed wall surface at 1/8" thickness.

b. Place material at the cove and form cove radius using and appropriate cove trowel.

c. Terminate bottom of cove base and install quartz flooring up to base.

IV. COVE BASE FOR Epoxy.com MORTAR AND Epoxy.com LASTIC SYSTEMS

Installations of an integral cove base with **Epoxy.com Solid Colored Floor Systems** are normally terminated at the floor line by cutting a straight line at the bottom of the cove and installing the system up to that point. The top of the cove is preferably terminated with a divider strip as pictured in the following pages.

A. Material Quantities

1. [*Epoxy.com #899*](#) Primer/Low Modulus Binder 1 gallon
2. *Epoxy.com #720* Cove Paste Binder 1.25 gallons
3. *Epoxy.com Blended Mortar Aggregate* 100 pounds
4. *Epoxy.com #60 Cove Powder* 1 quart

Recommended batch quantities

1. 1 QT *Epoxy.com #720* part A & 1 cup *Epoxy.com #720* part B
2. 21 pounds *Epoxy.com Blended Mortar Aggregate*
3. 1 pint *Epoxy.com Cove Powder*

Estimated Batch Coverage: 22-25 lineal feet at 1/8"

B. Installation--Priming

It is very important to prime the wall surface prior to installing cove base. Priming insures maximum adhesion to the prepared substrate and helps mixed cove material to "hang" on the wall.

1. Mixing **Epoxy.com #899 Low Modulus Epoxy Primer**

- a. Stir each component prior to mixing.
- b. Mix two (2) parts by volume of Part A (Base) with one (1) part by volume of Part B (Hardener) for three minutes with a low speed electric drill mixing paddle.
- c. If thinning is desired, add no more than one quart of xylene per gallon of epoxy at time of mixing.
- d. **Mix only that amount of material that can be used in 40 minutes.**

2. Application--Brush primer onto the wall surface.

3. Allow Primer to tack-up.

C. Installation--Cove Base

1. Mixing **Epoxy.com #720 Cove Paste Binder, Mortar Aggregate, & Cove Powder.**

- a. Stir each component prior to mixing.
- b. Mix four (4) parts by volume of Part A (Base) with one (1) part by volume of Part B (Hardener) for three minutes with a low speed electric drill mixing paddle.
- c. Transfer to KOL mixer and add *Epoxy.com Cove Powder* to the premixed *Epoxy.com #60*.

Note: Epoxy.com Resin Company recommends the use of a KOL Mixer when preparing cove base material. Insufficient mixing of cove base material will result in a stiff, dry, and hard to trowel blend that does not have sufficient wetting of aggregate to insure proper bonding to the substrate.

- d. Continue mixing while adding *Epoxy.com #77 Mortar Aggregate*
- e. Mix resin/aggregate mortar for 3 to 4 minutes or until aggregate uniformly is wet.

2. Application

- a. Trowel cove base mixture vertically onto primed wall surface at 1/4" thickness.
- b. Place material at the cove and form cove radius using and appropriate cove trowel.
- c. Terminate bottom of cove base and install mortar flooring up to base.

D. Installation--Grouting and Sealing

The grouting and sealing of the floor should be performed over the entire area receiving the system. The cove base should also receive the same grout and seal coats as the finished floor in order to provide proper performance and appearance. See installation instructions for each system to be installed.

**FOR INDUSTRIAL USE ONLY
KEEP AWAY FROM CHILDREN**

For more information please contact:

Epoxy.com.

352-489-1666 (Phone)

352-465-3497 (Fax)

info@epoxy.com

www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com 'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.

Many of our products are made on an individual order basis. Unless authorized in writing by Epoxy.com a division of Epoxy Systems, Inc. in writing before the material is made, there are no returns on items purchased from us, once the order has been processed, and the material made. In the event of authorized returns a restocking charge will be charged in the amount of 30% of the value of the material returned or \$150 whichever is greater. No returns on non-list priced items. All Returns are for merchandise (store) credit only, no cash or credit card credits. In the event of a return, buyer is responsible for the cost of shipping and handling in both directions.